



Technical Data Sheet

Hygenic[®] Extruded Rubber Tubing

Formulation: ET-563

Base Polymer: Dry Natural Rubber

Hygenic Extruded Natural Rubber Tubing is talc free, non-tacky, and has excellent tear resistance. It is a thermoset rubber which will retain its shape and strength even when reheated. ET-563 is specially formulated for high elongation. This product is manufactured in the US with equipment that can produce a wide variety of sizes and shapes including custom profiles, all with tight dimensional tolerances.

Typical Physical Properties

Tensile Strength	2000 psi
Ultimate Elongation	825%
100% Modulus	90 psi
300% Modulus	180 psi
500% Modulus	340 psi
Tear Resistance	140 lbf/in
Density	.94 gm/cm ³
Minimum Continuous use Temperature	-76 °F
Maximum Continuous use Temperature	250 °F
Durometer	35 ± 5 Shore A

Other Key Characteristics

Compression Set	Excellent
Abrasion Resistance	Excellent
Weather Resistance	Poor to Fair
Ozone Resistance	Poor
Odor	Fair

1245 Home Avenue | Akron, OH 44310 | Phone: 1.800.321.2135 | Website: Hygenic.com

NOTE: These physical properties are considered typical and may vary. Determination of product suitability is the sole responsibility of the user.

©2024 HYGENIC[®], HYTONE[™], and HYPERFORM[®] are trademarks or registered trademarks of The Hygenic Company, LLC, it's parent or sister subsidiaries, in the United States and other countries. All rights reserved.

Rev 0