



Technical Data Sheet

HYSYNAL[®] Synthetic Rubber Sheeting

Formulation: SC-736

Base Polymer: Dry Synthetic Rubber

HYSYNAL Synthetic Rubber Sheeting is a talc-free non-latex sheeting made from synthetic polyisoprene, a polymer known to have similar properties to natural rubber but without the associated natural rubber allergens. Like natural rubber, it offers excellent tensile strength, abrasion resistance and compression set.

Typical Physical Properties

Tensile Strength	2300 psi
Ultimate Elongation	650%
100% Modulus	150 psi
300% Modulus	360 psi
500% Modulus	1050 psi
Tear Resistance	105 lbf/in
Density	1.24 gm/cm ³
Minimum Continuous use Temperature	-20 to -60 °F
Maximum Continuous use Temperature	180 °F
Durometer	48 +/- 5 Shore A

Other Key Characteristics

Compression Set	Excellent
Abrasion Resistance	Excellent
Weather Resistance	Poor to Fair
Ozone Resistance	Fair
Odor	Fair

1245 Home Avenue | Akron, OH 44310 | Phone: 1.800.321.2135 | Website: Hygenic.com

NOTE: These physical properties are considered typical and may vary. Determination of product suitability is the sole responsibility of the user.

©2024 HYGENIC[®], HYTONE[™], and HYPERFORM[®] are trademarks or registered trademarks of The Hygenic Company, LLC, it's parent or sister subsidiaries, in the United States and other countries. All rights reserved.